



■ VERNICI PER LEGNO ■

Iridea

C O L O R A

STAINS
FOR WOOD



GL-GLW SOLVENT-BASED AND WATER-BASED GLAZES



GL400 - GLW400 Cherry



GL401 - GLW401 Blond walnut



GL402 - GLW402 Chestnut



GL403 - GLW403 Antique walnut



GL404 - GLW404 Walnut




GL405 - GLW405 Mahogany



GL406 - GLW406 Blue



GL407 - GLW407 Green



GL408 - GLW408 Dark walnut



GL409 - GLW409 Ebony

This sample was produced with a dilution ratio of 2:1 (GL:DILUTING AGENT) (GLW:WATER).

COLORS AVAILABLE ON REQUEST:

GLCA Concentrated solvent-based samples.

GLWCA Concentrated water-based samples.

GLRCA Rapid-drying concentrated solvent-based samples.

DESCRIPTION:

Wipeable, semi-transparent stains, available in both solvent-based (GL) and water-based (GLW) versions. Color the wood while endowing it with an antique look. Specially recommended for "period" or "rustic" furniture. GL-series glazes are ideal for achieving a highly market pore, while GLW-series glazes are ideal for achieving an even tone across the wooden surface. GLR-series glazes (rapid-drying solvent-based glazes) are available on request.

GL-SERIES APPLICATION:

Dilute to 30-50% with D1018 or D1024. Spray on and wipe after 2-4 minutes.

GLW-SERIES APPLICATION:

Dilute to 30-50% with water and, in Summer, add 5-10% of D1019. Spray on and wipe after 2-4 minutes.

GLR-SERIES APPLICATION:

Dilute to 30-50% with D1024. Spray on and wipe after 2-4 minutes.

APPLICATION OF SUBSEQUENT COATINGS:

Water-based or solvent-based nitro, polyurethane or acrylic coatings can be applied:

- GL after 12-24 hours of drying at 20°C.
- GLW after 8-12 hours of drying at 20°C.
- GLR after 4-6 hours of drying at 20°C.

LIGHT STABILITY:

EXCELLENT FOR INTERIORS.

GLH TRANSPARENT WATER-BASED GLAZES



GLH500 Cypriot earth




GLH501 Shadow earth



GLH502 Sienese earth



GLH503 African earth



GLH504 Cembra earth



GLH505 Volcanic earth

This sample was produced by 40% dilution with water.

COLORS AVAILABLE ON REQUEST:

GLHCA Concentrated samples.

DESCRIPTION:

Wipeable, transparent, water-based stains. Color the wood while endowing it with an antique look. Specially recommended for "period" or "rustic" furniture. Compared to GLW-series glazes, GLH-series glazes are more transparent but still have good unifying power.

APPLICATION:

Spray application, dilute to 20% with water for dark tones and up to 50% for light tones, and wipe after 1-3 minutes.

APPLICATION OF SUBSEQUENT COATINGS:

Nitro, polyurethane, acrylic and (mono and bicomponent) water-based coatings may be applied over the stains. Wait the stain has totally dried out (after 6-8 hours at 20°C) to avoid any problem.

LIGHT STABILITY:

EXCELLENT FOR INTERIORS.